31

RUST CONVERTER



SAFETY DATA SHEET AVAILABLE ON REQUEST

Always refer to the descriptions on labels. Keep out of reach of children. Respect the conditions of use.

Description

• Anti-corrosion formulation, 31 converts the rust into a protective barrier (organometallic compound) on all ferrous metals. It is perfectly suited for both uses, protecting parts exposed to oxidation and as a primer before painting.

Product information

Composition	Vinyl acrylate copolymer in aqueous phase, ethylene glycol.
Appearance/ Odour	Liquid / characteristic
рН	2.4
Density	1.11+/-0.03
Flash point	>70°C (>158°F)
Transport N° ONU	1805
Storage	Store in the original package. Keep container closed tightly.
Packaging	250ml / 1L / 5L

Directions for use

Compatibility / supports	metals
Méthodes	 The part to be treated should be brushed, degreased and free of mildew, rinsed with clean water and kept moist to assure the penetration into the rust.
	- 31 is used pure, with a brush, spray or by dipping.
	 Leave to dry 12 to 24 hours before painting. NB. A second coat may be needed for any very deep corrosion.
	- A paint coat is recommended, in the month following treatment, to insure the duration of effectiveness of 31.

Precautions for use

 \bullet Causes skin irritation. Causes serious eye irritation. May cause respiratory irritation.

Before use: Always carry out a test on a small area.

